



TEST REPORT

DATE: 03-13-2014

TEST NUMBER: 0206170

CLIENT	The Tyred Flooring Company
---------------	----------------------------

TEST METHOD CONDUCTED	ASTM E303 Test Method for Measuring Surface Frictional Properties using the British Pendulum Tester
------------------------------	---



DESCRIPTION OF TEST SAMPLE	
IDENTIFICATION	Next Step Walk Soft (4+8) Muskwood 12 x12 - Product D
CONSTRUCTION	Laminated 4mm top + 8 mm Soft Black Mat

PROCEDURE

This test method provides the method of using the British Pendulum Tester to measure the "skid resistance" or frictional properties of a test surface. The dynamic pendulum impact tester is used to measure energy loss when a rubber edge slider is propelled over a test surface. The test material was tested in 4 directions with the average BPN (British Pendulum Number) reported. A lower BPN indicates a more slippery surface.

TEST RESULTS

CONDITION	BPN
Rubber Heel Tested Dry	106.0
Rubber Heel Tested Wet	103.0

APPROVED BY:

This report is provided for the exclusive use of the client to whom it is addressed. It may be used in its entirety to gain product acceptance from duly constituted authorities. This report applies only to those samples tested and is not necessarily indicative of apparently identical or similar products. This report, or the name of Professional Testing Laboratory Inc. shall not be used under any circumstance in advertising to the general public.